



FOLIO SHEETS

60g/m² 70g/m² 80g/m² 90g/m² Tolerance

OPTICAL PARAMETERS

	ISO 11475	155	155	155	155	+/- 3
	ISO 2470	109	109	109	109	+/- 3
	ISO 2471	87	91	94	95	- 2

PHYSICAL PARAMETERS

	ISO 536	60	70	80	90	+/- 2 (60) +/- 3 (70) +/- 4 (80/90)
	ISO 534	80	92	106	116	+/- 3
	ISO 2493	50/20	70/25	100/35	140/50	Minimum
	ISO 1924/2	4,0	4,5	4,5	5,0	Minimum
	ME-PAP-010	25	30	30	30	Minimum
	ISO 5636/3	1700	1700	1700	1700	Maximum
	ISO 8791/2	150	150	150	150	+/- 40
	ISO 287	6,2	6,2	6,0	6,0	+/- 1,0

Additional Information



FOLIO SHEETS

100g/m² 110g/m² 120g/m² Tolerance

OPTICAL PARAMETERS

	ISO 11475	155	155	155	+/- 3
	ISO 2470	109	109	109	+/- 3
	ISO 2471	96	97	98	- 2

PHYSICAL PARAMETERS

	ISO 536	100	110	120	+/- 4
	ISO 534	128	141	150	+/- 3
	ISO 2493	180/70	220/90	260/110	Minimum
	ISO 1924/2	5,5	5,5	6,0	Minimum
	ME-PAP-010	30	30	30	Minimum
	ISO 5636/3	1700	1700	1700	Maximum
	ISO 8791/2	150	150	150	+/- 40
	ISO 287	5,8	5,8	5,8	+/- 1,0

Additional Information



FOLIO SHEETS

135 g/m² 150 g/m² 170 g/m² 190 g/m² Tolerance

OPTICAL PARAMETERS

	ISO 11475	155	155	155	155	+/-3
	ISO 2470	109	109	109	109	+/-3
	ISO 2471	95	97	98	98	Minimum

PHYSICAL PARAMETERS

	ISO 536	135	150	170	190	+/-5%
	ISO 534	155	172	205	230	+/-6%
	ISO 8791/2	150	150	200	200	+/-50 -75/+50
	ISO 287	6	6	6	6	+/-1%

Additional Information



FOLIO SHEETS

225 g/m² 250 g/m² 300 g/m² 350 g/m² Tolerance

OPTICAL PARAMETERS

	ISO 11475	155	155	155	155	+/-3
	ISO 2470	109	109	109	109	+/-3
	ISO 2471	98	98	98	98	Minimum

PHYSICAL PARAMETERS

	ISO 536	225	250	300	350	+/-5%
	ISO 534	275	305	365	425	+/-6%
	ISO 8791/2	200	200	200	200	-75/+50
	ISO 287	6	6	6	6	+/-1%

Additional Information



FOLIO SHEETS

75 g/m² 80 g/m² 90g/m² 100g/m² 120g/m² Tolerance

OPTICAL PARAMETERS

	ISO 11475	164	164	164	164	164	+/- 3
	ISO 2470	111	111	111	111	111	+/- 3
	ISO 2471	93	95	96	97	98	- 2

PHYSICAL PARAMETERS

	ISO 536	75	80	90	100	120	+/- 3 (75) +/- 4 (80-120)
	ISO 534	103	108	115	118	126	+3 / -2 (75) +/- 3 (80,90) +/- 2 (100/120)
	ISO 2493	100/35	120/45	150/60	170/60	220/90	Minimum
	ISO 1924/2	5,0	6,0	6,5	7,0	8,0	Minimum
	ME-PAP-010	25	30	30	40	45	Minimum
	ISO 5636/3	1700	1700	1700	1700	1700	Maximum
	ISO 8791/2	180	150	150	100	50	+/- 40 (75/80/90) +/- 30 (100/120)
	ISO 287	5,0	5,0	5,0	5,0	5,0	+0,3 / -0,4 %

Additional Information



FOLIO SHEETS

135 g/m² 160 g/m² 250 g/m² Tolerance

OPTICAL PARAMETERS

	ISO 11475	164	164	164	+/-3
	ISO 2470	111	111	111	+/-3
	ISO 2471	96,5	97,5	98	Minimum

PHYSICAL PARAMETERS

	ISO 536	135	160	250	+/-5%
	ISO 534	140	170	275	+/-5 % (160) +/- 6% (135,250)
	ISO 8791/2	50	50	80	≤ 90 (135,160) ≤ 130 (250)
	ISO 287	5	5	6	+/- 0,5% (135,160) -1%/ + 0,5% (250)

Additional Information
